



801-0711 | RS PRO



Pile lithium RS PRO - CR123A - 3V - 7Ah

Réf 801-0711

8.00€^{TTC*}

Voir le produit : https://www.domomat.com/55998-pile-lithium-rs-pro-cr123a-3v-7ah-rs-pro-801-0711.html


Le produit Pile lithium RS PRO - CR123A - 3V - 7Ah est en vente chez Domomat!





Datasheet


LITHIUM BATTERY



•	
	(T 7)
	(V)
	(')

Voltage


Temperature characteristics(20mA)



ENGLISH

Voltage (V)


Pulse discharge characteristics



Model CR123A 3V Nominal Voltage Nominal 1700mAh Capacity Standard 20mA Discharge Current Φ16.7×34.1mm Dimension Weight 15.8g Temperature -40~60°C range

Voltage (V)

Typical discharge characteristics



RS, Professionally Approved Products, gives you professional quality parts across all products categories. Our range has been testified by engineers as giving comparable quality to that of the leading brands without paying a premium price.



ENGLISH

. Model Number : CR-123A

2. Nominal Voltage : 3 V

3. Nominal Capacity : 1700 mAh

(Nominal capacity is based on standard discharge current and cutoff Voltage down

to 1.5V at $20\pm5^{\circ}$ C)

4. Standard Discharge Current : 20 mA

5. Max. Continuous Discharge Current : 1500 mA

6. Construction

6.1 Appearance, Dimensions : There shall be no noticeable deformation.

The dimensions shall be according to the

attached drawings.

6.2 Weight : Approx. 15.8g

7. Performance

7.1 Open Circuit Voltage : Min. 3 V

7.2 Duration 1. (at $20\pm2^{\circ}$)

7.2.1 Pulse Discharge Conditions : Population Mean ≥ 2000 cycles

Pulse Current : 900 mA

One Cycle : 3 seconds on, 27 seconds off

Cut Off V. : 1.55 V

7.3 Duration 2. (at $-20\pm2^{\circ}$ C)

7.3.1 Pulse Discharge Conditions : Population Mean ≥ 1100 cycles

Pulse Current : 900 mA

One Cycle : 3 seconds on, 27 seconds off

Cut off V. : 1.2 V

7.4 Temperature Range : Discharge -40 to $60^{\circ}\mathrm{C}$

Storage −20 to 45°C

7.5 Leakage Resistance : The battery shall not show leakage or

salting which harms performance.

8. PTC (Positive Temperature Coefficient) Device Performance

8.1 Appearance : There shall be no noticeable deformation

and/or scratches.

8.2 Resistance : The resistance shall be between 10 to 70

 $m\Omega$ (no load).

When 5 A flows, the resistance shall be

more than $10~\Omega$ before 80 seconds.

9. Test Conditions, Measuring Instruments and Measuring Methods

9.1 Test Conditions

: If not otherwise specified,

Temperature : $25\pm5^{\circ}$ C Humidity : $65\pm10^{\circ}$

CR123A-1



: Internal Impedance : More than $1M\,\Omega$

Accuracy : Less than 0.25% : Accuracy : less than 0.25%

: Accuracy : less than 0.25% : Sensitivity : More than 100 mg

9.2 Measuring Instruments

i) Volt Meter

ii) Caliper

iii) Balance

9.3 Measuring Method

i) Outer Dimensions

ii) Weight

iii) Appearance

iv) Open Circuit Voltage

v) Operating Time (Duration)

vi) Vibration Resistance

vii) Leakage Resistance

: This shall be measured with the caliper described in Item 9.2 ii).

: This shall be measured with the balance described in Item 9.2 iii).

: Deformation or tarnish shall be visually checked.

: This shall be measured with the volt meter described in Item 9.2 i).

: Operating time shall be measured with cycles until terminal voltage reaches the specified cut-off voltage.

: Amplitude ; 2 mm

Number of Vibrations: 1000 rpm.

Directions ; X, Y, Z

Time: 30 minutes in each direction

: Heat cycle test

Leakage, appearance and outer dimensions

shall be checked after 10 cycles according to MIL-STD-202E-106D.

The battery shall be kept in a dry place. It should not show any dew point

when stored in this condition.

10. Precautions for use

- 1) A battery shall not be stored at temperatures in excess of 45℃. Storage at less than 30℃ is recommended. Storage at less than -40℃ can deform the plastic parts and may cause a leakage. To prevent self-discharge caused by corrosion, or decrease of insulation, humidity during storage shall be less than 70%.
- 2) The battery has an explosion resistant construction. But the following cautions should be taken, because combustible materials such as lithium metal and organic electrolyte are contained in the battery.
 - * Do not use except in applicable model or equipment.
 - * Do not connect more than three cells in series.
 - * Do not mix different types (chemistries) of batteries.
 - * Do not short circuit.
 - * Do not dispose in fire.
 - * Do not charge.
 - * Do not disassemble.
 - * Do not connect the wrong polarity (+, -)
- 3) Keep away from heat source of flame.
- 4) The battery shall not be washed by ultrasonic wave washer.

CR123A-2